

	Test method	Requirements	Average test results from running production				
			uni 2.0 mm	eco 2.0 mm sentica 2.0 mm signa 2.0 mm stone 2.0 mm valua 2.0 mm lona 2.0 mm	unifa 2.0 mm	ultra grip 2.0 mm	sentica 3.0 mm signa 3.0 mm valua 3.0 mm
CE conformity	EN 14041		← Manufacturer: nora systems GmbH, D-69469 Weinheim →				
DoP-No.	EN 14041		0018	0016	0010	0016	0017
Thermal conductivity	EN 10456	$\lambda = 0.17 \text{ W/(m·K)}$	← Fulfilled →				
Dynamic coefficient of friction	EN 13893	DS	← Suitable for underfloor heating systems →				
Reaction to fire	EN 13501-1	Not bonded	← Fulfilled →				
Reaction to fire	EN 13501-1	Bonded on mineral subfloor	B _f s1	B _f s1, bonded	C _f s1	B _f s1, bonded	C _f s1
Reaction to fire	EN 13501-1	Bonded on mineral subfloor	B _f s1	B _f s1	C _f s1	B _f s1	B _f s1

Properties acc. to EN 1817/EN 1816

Thickness	EN ISO 24346	Mean value without foam backing $\pm 0.15 \text{ mm}$	2.0 mm	2.0 mm	2.0 mm	3.0 mm	-	
		Mean value with foam backing $\pm 0.20 \text{ mm}$	-	-	-	-	4.0 mm	
Dimensional stability	EN ISO 23999	$\pm 0.4 \%$	← $\pm 0.3 \%$ →					
Cigarette-burn resistance	EN 1399	Procedure A (stubbled out) level ≥ 4 Procedure B (burning) level ≥ 3	← Fulfilled →					
Flexibility	EN ISO 24344, procedure A	Mandrel diameter 20 mm, no fissuring	← Fulfilled →		Not fulfilled	Fulfilled	-	← Fulfilled →
Hardness	ISO 48-4	$\geq 75 \text{ Shore A}$	94 Shore A	92 Shore A	90 Shore A	92 Shore A	85 Shore A	
Residual indentation	EN ISO 24343	Mean value $\leq 0.15 \text{ mm}$ at thickness $< 2.5 \text{ mm}$	0.03 mm	0.03 mm	0.05 mm	-	-	
		Mean value $\leq 0.20 \text{ mm}$ at thickness $\geq 2.5 \text{ mm}$	-	-	-	0.03 mm	-	
		acoustic: Mean value $\leq 0.25 \text{ mm}$	-	-	-	-	0.25 mm	
Abrasion resistance at 5 N load	ISO 4649, procedure A	$\leq 250 \text{ mm}^3$	130 mm ³	150 mm ³	90 mm ³	150 mm ³	130 mm ³	
Colour fastness to artificial light	ISO 105-B02, procedure 3, test conditions 6.1 a)	At least level 6 on the blue scale; \geq level 3 on the grey scale	← Grey scale \geq level 3 acc. to ISO 105-A02 →					
Classification	EN ISO 10874	Commercial/Industrial	34/42	34/42	34/42	34/43	33/-	

Additional technical properties

Toxicity of fire gases	DIN 53436		← Carbonisation gases are non-toxic →				
Anti-slip properties	DIN 51130	According to BGR 181	R 9	stone Art. 149/249 + signa Art. 1690/2690: R 10 Others: R 9	R 11	R 9	stone acoustic: R 10 Others: R 9
	DIN 51097		-	stone Art. 149/249 + signa Art. 1690/2690: A; B	A; B; C	-	-
	BS 7976 TRRL Pendulum		-	-	36+ Wet & dry	-	-
	SATRA TM 144		-	-	Wet: > 0.6 Dry: > 0.45	-	-
Improvement in footfall sound absorption	ISO 10140-3		6 dB	6 dB	7 dB	8 dB	20 dB
Effect of chemicals	EN ISO 26987		← Resistant depending on concentration and time of exposure* →				
Electrical insulation properties	EN 1081 R1		$> 10^9 \text{ Ohm}$	$> 10^{10} \text{ Ohm}$	$> 10^9 \text{ Ohm}$	$> 10^{10} \text{ Ohm}$	$> 10^9 \text{ Ohm}$
Electrical propensity when walked upon	EN 1815		← Antistatic, charging in case of rubber soles $< 2 \text{ kV}$ →				
Effect of a castor chair	EN 425		← Suitable if castor wheels, type W, according to EN 12529 are used →				

* In case of increased impact of oils, grease, acids, alkalis and other aggressive chemicals please contact us.

EN 1817: Specification for homogeneous and heterogeneous smooth elastomer floor coverings

EN 1816: Specification for homogeneous and heterogeneous smooth elastomer floor coverings with foam backing

Colour variations due to different production batches as well as technical alterations to improve the product have to be accepted.